



28 GNN

Tested according EN 12825

General characteristics

Measurements	600 x 600 mm
Weight	+/- 16 kg
Core	28 mm calcium sulphate Knauf - density > 1500 kg/m³
Bottom side	bare
Top side	bare
Edge banding	PVC 0,6 mm

System characteristics

Class of element	1
Ultimate load	>=4kN
Safety factor	2
Point load	2kN
Class of deflection (max. 2,5 mm deflection by 2kN)	A
Divided load per m² (theoretical value)	10kN-15kN / m²

Fire characteristics

Fire resistance	F30 according DIN 4102-2
Fire reaction	class A2 according DIN 4102-1

Electrical characteristics

Electrical resistance	>10 ⁷ Ohm
Other values are possible when using conductive edge banding and conductive glue.	

Jansen Products NV
Fabriekstraat 4
3670 Meeuwen
BELGIUM

Tel : +32 11 79 33 00
Fax : +32 11 79 33 01
Info@jansenproducts.be
www.groupjansen.com

 **JANSEN**
products